

ISO 95+™ GL Insulation

Item Description

Flat and Tapered Polyiso Boards

Flat Boards: 4' x 4' (1.22 m x 1.22 m)

4' x 8' (1.22 m x 2.44 m)

Tapered Boards: 4' x 4' (1.22 m x 1.22 m)

Slope range: 1/16" per foot (.5%) to 1/2" per foot (4%)

Thickness range: 0.5" (12.7 mm) to 4.0" (101.6 mm)

Meets or exceeds performance requirements of ASTM C 1289, Type II, Class 1

Product Information

Description:

Firestone ISO 95+ GL flat and tapered roof insulation consists of a closed-cell polyiso foam core laminated to a black glass reinforced mat facer on both major surfaces. Flat and tapered ISO 95+ GL insulation provides outstanding thermal performance on commercial roofing applications, while providing positive rooftop drainage to help eliminate ponding water when tapered ISO 95+ GL insulation is used.

Method of Application:

- 1. Insulation shall be neatly fitted to all roof penetrations, projections and nailers.
- 2. No more insulation shall be installed than can be covered with membrane and completed before the end of each day's work or before the onset of inclement weather.
- 3. Firestone ISO 95+ GL board may be installed using:
 - Firestone fasteners and plates
 - o NOTE: For ballasted systems, the top layer of Firestone insulation may not be mechanically attached.
 - Hot asphalt (requires a cover board)
 - Firestone approved insulation adhesives
 - I.S.O. Twin Pack™
 - o I.S.O. Stick™
 - o I.S.O. Spray™ R
 - o I.S.O. FIX™ II


Acceptable Immediate Substrates:

- 3,000 psi Structural concrete (must be clean, dry, and properly cured)
- Steel deck (min 22 ga)
- Plywood and OSB (min ½")
- Lightweight concrete
- Gypsum deck (min 2")

NOTE: Please consult the Design Guides and QuickSpecs online at www.firestonebpco.com to review specific information regarding the assembly.

Storage:

- Keep insulation dry at all times
- Elevate insulation above the deck or ground
- · Cover insulation with waterproof tarps





ISO 95+™ GL Insulation

Precautions:

- Polyiso foam will burn if exposed to a flame of sufficient heat and intensity. Keep away from heat, sparks, and open flames.
- Protect against dust that may be generated during installation.
- Refer to Safety Data Sheet (SDS) for additional information.
- Take care when transporting and handling Firestone insulation to avoid physical damage.

Specification Compliance:

ASTM C1289, Type II, Class 1 UL Classified – UL1256 FM Class 1 Approved Manufactured in an ISO 9001 Registered Facility CAN/ULC-S704, Type 1, Class 3









CCMC 13274-L

Bristol, Ct

Youngwood, PA

LEED® Information:

See Recycled Content in table below.

Manufacturing Locations: Florence, KY

Florence, KY Corsicana, TX
De Forest, WI Salt Lake City, UT

Jacksonville, FL

NOTE: Miami Dade Classified polyiso is only produced in the Jacksonville, FL and Youngwood, PA facilities.

Typical Properties (Meets ASTM C 1289, Type II, Class 1)

	· · · · · · · · · · · · · · · · · · ·	
Property	ASTM Test Method	Firestone Typical Performance
Compressive Strength:	D1621	20 psi (138 kPa)
Density:	D1622	2 pcf (32 kg/m ³)
Dimensional Stability:	D2126	<2%
Moisture Vapor Transmission:	E96	<1 perm (<57.5 ng/(Pa•s•m²))
Water Absorption:	C209	<1% by volume
Service Temperature:		-100 to 250 °F (-73 to 121°C)
Flame Spread:	E84	Index 50
Smoke Development:	E84	Index 160 - 180

^{*25} psi (172 kPa) available upon request.



ISO 95+™ GL Insulation

Thickness* (R-		(R-Value)	Max Flut	te Span	Approx. Recycled Content		
inches	mm	**	inches	mm	Post Consumer	Post Industrial	Total
1.0	25.40	5.7	2.62	66.67	37%	15%	52%
1.1	27.94	6.3	2.62	66.67	36%	15%	51%
1.2	30.48	6.8	2.62	66.67	34%	15%	49%
1.3	33.02	7.4	3.67	93.34	32%	15%	47%
1.4	35.56	8.0	3.67	93.34	30%	15%	45%
1.5	38.10	8.6	4.37	111.12	29%	15%	44%
1.6	40.64	9.1	4.37	111.12	27%	15%	42%
1.7	43.18	9.7	4.37	111.12	26%	15%	41%
1.75	44.45	10.0	4.37	111.12	26%	15%	41%
1.8	45.72	10.3	4.37	111.12	25%	15%	40%
1.9	48.26	10.8	4.37	111.12	24%	15%	39%
2.0	50.80	11.4	4.37	111.12	24%	15%	39%
2.1	53.34	12.0	4.37	111.12	22%	15%	37%
2.2	55.88	12.6	4.37	111.12	21%	15%	36%
2.25	57.15	12.9	4.37	111.12	21%	15%	36%
2.3	58.42	13.2	4.37	111.12	21%	15%	36%
2.4	60.96	13.8	4.37	111.12	20%	15%	35%
2.5	63.50	14.4	4.37	111.12	20%	15%	35%
2.6	66.04	15.0	4.37	111.12	19%	15%	34%
2.7	68.58	15.6	4.37	111.12	18%	15%	33%
2.75	69.85	15.9	4.37	111.12	18%	15%	33%
2.8	71.12	16.2	4.37	111.12	18%	15%	33%
2.9	73.66	16.8	4.37	111.12	17%	15%	32%
3.0	76.20	17.4	4.37	111.12	17%	15%	32%
3.1	78.74	18.0	4.37	111.12	16%	15%	31%
3.2	81.28	18.6	4.37	111.12	16%	15%	31%
3.25	82.55	18.9	4.37	111.12	16%	15%	31%
3.3	83.82	19.2	4.37	111.12	16%	15%	31%
3.4	86.36	19.9	4.37	111.12	15%	15%	30%
3.5	88.90	20.5	4.37	111.12	15%	15%	30%
3.6	91.44	21.1	4.37	111.12	14%	15%	29%
3.7	93.98	21.7	4.37	111.12	14%	15%	29%
3.75	95.25	22.0	4.37	111.12	14%	15%	29%
3.8	96.52	22.3	4.37	111.12	14%	15%	29%
3.9	99.06	23.0	4.37	111.12	14%	15%	29%
4.0	101.60	23.6	4.50	114.30	14%	15%	29%

^{*}Other thicknesses available upon request.

Please contact Quality Building Services Technical Department at 1-800-428-4511 for further information.

This sheet is meant to highlight Firestone products and specifications and is subject to change without notice. Firestone takes responsibility for furnishing quality materials which meet published Firestone product specifications or other technical documents, subject to normal roof manufacturing tolerances. Neither Firestone nor its representatives practice architecture. Firestone offers no opinion on and expressly disclaims any responsibility for the soundness of any structure. Firestone accepts no liability for structural failure or resultant damages. Consult a competent structural engineer prior to installation if the structural soundness or structural ability to properly support a planned installation is in question. No Firestone representative is authorized to vary this disclaimer.

Firestone Building Products | Sales: (800) 428-4442 | Technical (800) 428-4511 | www.firestonebpco.com

^{**}R- values provide a 15-year time-weighted average in accordance with CAN/ULC-S770.